

LULI GROUP CORPORATION LTD

Technical Specifications for All poplar plywood

No	Property	Unit	Standard	Value of Test
1	Size etc tolerance	mm	EN636	Thickness: +/-0.5-1mm, Width/length: +3mm.
2	Glue type	Phenolic glue		24hours in boiling water
3	Density Kg / m3	Kgs/m3.		520-580
4	Moisture content %	%		12%(14% max)
5	Bending strength	Mpa		45 40
6	Bending Modules of Elasticity	Mpa		5100 4500
7	Formaldehyde emission	mg/L.		E1<1.5mg/L



Houzhen Town, Shouguang City, Shandong Province, 262724