

LULI GROUP CORPORATION LTD

Technical Specifications for bruto bamboo plywood

No	Property	Unit	Standard	Value of Test
1	Size etc tolerance	mm	EN636	Thickness:+/-1-1.5mm, Width/length:+3mm.
2	Glue type	Phenolic glue		72hours in boiling water
3	Density Kg / m3	Kgs/m3.		800-850
4	Moisture content %	%		12%(15% max)
5	Bending strength	Mpa		65
6	Bending Modules of Elasticity	Mpa		6000
7	Formaldehyde emission	mg/L.		E1<1.5mg/L

Houzhen Town, Shouguang City, Shandong Province, 262724

